



**PAVUS**<sup>®</sup>  
FIRE TESTING INSTITUTE

**PAVUS, a.s.**

AUTHORIZED BODY AB 216

NOTIFIED BODY 1391

ACCREDITED CERTIFICATION BODY FOR PRODUCT CERTIFICATION No. 3041

**Address:**  
Prosecká 412/74, 190 00 Prague 9 –  
Prosek  
Phone: 286 019 587, E-mail: mail@pavus.cz  
http://www.pavus.cz

**Branch:**  
Fire testing laboratory Veselí nad Lužnicí  
Čtvrť J. Hybeše 879, 391 81 Veselí nad Lužnicí  
Phone: 381 477 418, E-mail: veseli@pavus.cz

# REACTION TO FIRE CLASSIFICATION REPORT

**The object of  
classification:**

*Construction products excluding floorings and linear pipe  
thermal insulation products  
in accordance with EN 13501-1:2018, clause 11*

**Report No:**

**PK1-01-23-031-E-0**

**Type and product  
name:**

*Textile Softimage Contrast<sup>®</sup> Art. No. 599150 15\**

**Sponsor:**

**PONGS GROUP GmbH & Co. KG**  
*Bahnhofstraße 21  
07919 Pausa - Mühltröfz  
Germany*

**Issuing organization:**

**PAVUS, a.s.**  
*Accredited certification body for products No 3041  
– Accreditation issued by Czech Accreditation Institute,  
Public Service Company  
– Certificate of Accreditation No. 588/2022*

*Prosecká 412/74  
190 00 PRAHA 9  
Czech Republic*

*Order No Z210230160*

**Date of issue:**

*2023-05-19*

**Copies in total:**

*2*

**Copy number:**

*1*

**Pages in total:**

*4*

## 1 INTRODUCTION

- 1.1 This classification report defines the classification assigned to *Softimage Contrast*<sup>®</sup> Art. No. 599150 15\* in accordance with the procedures given in EN 13501-1:2018.
- 1.2 This classification report has 4 pages and it can be used or reproduced as a whole only.

## 2 DETAILED INFORMATION ON THE PRODUCT TO BE CLASSIFIED

### 2.1 General

The product *Softimage Contrast*<sup>®</sup> Art. No. 599150 15\* is made by the company PONGS GROUP GmbH & Co. KG, Bahnhofstraße 21, 07919 Pausa - Mühltruff, Deutschland. It is used free-hanging for cladding of walls and ceilings, digital print, promotional materials, banners, decoration, fairs etc.

### 2.2 Product description

Thickness: 0.37 mm  
 Mass per unit area: 210 g/m<sup>2</sup>  
 Colour: white side intended to printing, black back side  
 Composition: 100 % PES (polyester)

## 3 REPORTS AND RESULTS IN SUPPORT OF THIS CLASSIFICATION

### 3.1 Reports

Name of the Laboratory Address Accreditation number:	Name of sponsor of the Test Report	Report number Date of issue	Test method
PAVUS, a. s. Veselí nad Lužnicí ATL No 1026	PONGS GROUP GmbH & Co. KG Bahnhofstraße 21 07919 Pausa - Mühltruff Deutschland	Pr-23-1.081 2023-05-19	EN 13823:2020+A1:2022
		Pr-23-1.082 2023-05-19	EN ISO 11925-2:2020

### 3.2 Results

Test method	Parameter	Number of tests	Results	
			Continuous parameter-mean	Compliance with parameters
EN 13823+A1 white side	FIGRA <sub>0,2 MJ</sub> (W/s)	3	1.9	≤ 120 (B)
	THR <sub>600s</sub> (MJ)		0.4	≤ 7.5 (B)
	LFS < edge of specimen		-	yes (B)
	SMOGRA (m <sup>2</sup> /s <sup>2</sup> )		0.0	≤ 30 (s1)
	TSP <sub>600s</sub> (m <sup>2</sup> )		21.0	≤ 50 (s1)
	non-occurring of flaming droplets/particles		-	yes (d0)

Test method	Parameter	Number of tests	Results	
			Continuous parameter-mean	Compliance with parameters
EN 13823+A1 black side	FIGRA <sub>0,2 MJ</sub> (W/s)	1	0.0	≤ 120 (B)
	THR <sub>600s</sub> (MJ)		0.1	≤ 7.5 (B)
	LFS < edge of specimen		-	yes (B)
	SMOGRA (m <sup>2</sup> /s <sup>2</sup> )		0.0	≤ 30 (s1)
	TSP <sub>600s</sub> (m <sup>2</sup> )		20.7	≤ 50 (s1)
	non-occurring of flaming droplets/particles		-	yes (d0)
EN ISO 11925 - 2 Surface exposure - white side	F <sub>s</sub> ≤ 150 mm up to 60 s Filter paper non-ignition	6	- -	yes (B) yes (d0)
EN ISO 11925 - 2 Edge exposure - white side	F <sub>s</sub> ≤ 150 mm up to 60 s Filter paper non-ignition	6	- -	yes (B) yes (d0)
EN ISO 11925 - 2 Surface exposure - black side	F <sub>s</sub> ≤ 150 mm up to 60 s Filter paper non-ignition	8	- -	yes (B) yes (d0)
EN ISO 11925 - 2 Edge exposure - black side	F <sub>s</sub> ≤ 150 mm up to 60 s Filter paper non-ignition	6	- -	yes (B) yes (d0)

## 4 CLASSIFICATION AND FIELD OF APPLICATION

### 4.1 Classification references

This classification was carried out in conformity with EN 13501-1:2018.

### 4.2 Classification

The product *Softimage Contrast® Art. No. 599150 15\** in relation to its reaction to fire behaviour is classified:

**Reaction to fire class: B – s1, d0**

### 4.3 The field of application

This classification is valid for the following product parameters:

Thickness: 0.37 mm  
 Mass per unit area: 210 g/m<sup>2</sup>  
 Colour: white side intended to printing, black back side  
 Composition: cannot be changed

This classification applies for the following end-use applications:

Substrate: free situated product without a substrate or with substrates of reaction to fire classes A1  
 Way of fixing: mechanically with fittings of reaction to fire classes A1  
 Joints: without joints  
 Sides: bilaterally

## 5 RESTRICTIONS

This classification is valid unless the conditions, under which it was issued, have been changed (i.e., until the materials used, the composition or design of the product or the technical regulations relating to the product change).

The sponsor may request the issuing authority to review the influence of changes on the classification validity.

This classification document does not represent type approval or certification of the product.

*Elaborated by:*



.....  
**Lenka SOBOTOVÁ**  
Fire testing laboratory

**PAVUS, a.s.**  
Čtvrť J. Hybeše 879  
391 81 Veselí nad Lužnicí  
IČ: 60193174; DIČ: CZ60193174  
(9)

*Approved by:*



.....  
**Jan TRIPES**

